

BauderTHERMOFOL M20

Technical data sheet

Type of application		PVC-P waterproofing membrane for loose laying, mechanically fixed only
Surface	Top	light grey similar RAL 7035
	Bottom	black
Reinforcement	Type	Synthetic PES fibre fabric
Article number		6320 0000

Characteristic	Test method	Value	
Visible defects	EN 1850-2	no visible defects	
Length	EN 1848-2	20 m (-0/+5%)	
Width	EN 1848-2	1,5 m (-0,5/+1 %)	
Straightness	EN 1848-2	< 50 mm	
Flatness	EN 1848-2	< 10 mm	
Mass per unit area	EN 1849-2	2,4 kg/m ² (-5/+10%)	
Effective thickness	EN 1849-2	2,0 mm (-5/+10%)	
Water tightness	EN 1928 Method B	passed	
External fire performance	CEN/TS 1187	npd	
Reaction to fire	EN 13501-1	class E according EN 13501-1	
Joint peel resistance	EN 12316-2	≥ 200 N	
Joint shear resistance	EN 12317-2	≥ 600 N	
Tensile force	md	EN 12311-2 A	≥ 1000 N/50mm
	cd	EN 12311-2 A	≥ 1000 N/50mm
Elongation at maximum tensile force	md	EN 12311-2 A	≥ 20 %
	cd	EN 12311-2 A	≥ 20 %
Resistance to impact	hard surface	EN 12691	> 600mm
	soft surface	EN 12691	> 900 mm
Resistance to static load	hard surface	EN 12730	≥ 20 kg
	soft surface	EN 12730	≥ 20 kg
Tear resistance	EN 12310-2	> 250 N	
Dimensional stability	EN 1107-2	< 0,3 %	
Foldability at low temperature	EN 495-5	≤ -30 °C	
UV exposure (> 1000 h)	EN 1297	passed	
Hail resistance	hard surface	EN 13583	40 m/s
	soft surface	EN 13583	54 m/s
Water vapour properties ¹⁾	EN 1931	20000 (±30%)	
Nail Shaft test	EN 12310-1	> 500 N	

¹⁾ The characteristic meant is the moisture resistance factor μ .



Identification number of the certification body: 0800
09
 CPR – 51213; EN 13956
 Unique Code: BauderTHERMOFOL M20 - 03