

SINTOFOIL RC

(€

Description

Synthetic waterproofing membrane produced by co-extruding a UV resistant elastomerised TPO/FPA thermoplastic olefin and flexible polypropylene alloy with a synthetic inorganic composite reinforcing mat. The membrane features contrasting colours on its upper and lower faces, providing a signal layer so that any damage occurring during or after installation will be immediately apparent. Also available in Reflecta White version with the upper side of the membrane (top) manufactured with the Reflecta White treatment, developed in mass in the entire layer that covers the top of the reinforcement. This process enhances the reflectance and emission features giving the waterproof covering Solar Reflectance Index (SRI) values that reach 102%. SINTOFOIL RC membranes comply with CE marking requirements, if applicable.

System certifications

QMS (Quality Management System) certification according to ISO 9001.

Product certifications

Regulation CPR 305/2011/EU.

FM certification.

EELAB certification.

This product can contribute to acquiring points in terms of LEED accreditation.

Fields of application

Specific use

- Mechanically retained waterproofing for:
 - exposed roofs.
- Waterproofing layers loose laid under heavy-duty fixed or movable protection for:
 - roofing exposed to foot and vehicular traffic;
 - inverted roofs.

Note: Given the versatility and reliability of SINTOFOIL membranes, other applications can be developed with the assistance of the IMPER ITALIA srl – Rubberfuse Division Technical Services.

Application

Sintofoil membranes are applied through hot air gun on their overlapping joints, as no adhesives or other materials of any kind are required. Design solutions and application methods are illustrated in the technical manual published by the RUBBERFUSE Division. Waterproofing systems employing SINTOFOIL membranes should be laid by installers authorised by RUBBERFUSE Division Technical Services.



| TECHNICAL FEATURES(1) | | | | | | | | | | | |
|--|--|------------|-----------|--|-----------|------|------|--|--|--|--|
| Features | EN Standards | U.M. | Tolerance | Values | | | | | | | |
| Standard thickness | 1849-2 | mm | (-5/+10%) | 1,2 | 1,5 | 1,8 | 2,0 | | | | |
| Density | 1849-2 | kg/m² | (-5/+10%) | 1,14 | 1,39 | 1,67 | 1,85 | | | | |
| SRI – Solar Reflectance Index | ASTM Stardard E1980 | % | | 102(*) | | | | | | | |
| Tensile properties | | | | | | | | | | | |
| • Tensile strength L/T | 12311-2 | N/50 mm | | 1100 | | | | | | | |
| • Elongation at break L/T | 12311-2 | % | | 25 | | | | | | | |
| Dimensional stability | 1107-2 | % | | ≤ 0.1 | | | | | | | |
| Cold flexibility | 495/5 | °C | | ≤-40 ⁽²⁾ | | | | | | | |
| Tear resistance L/T | 12310/1 | N | | 550/600 | | | | | | | |
| Water vapour permeability | 1931 | | | 50.000 | | | | | | | |
| Resistance to static loading | 12730/B | kg | | ≥25 | | | | | | | |
| Resistance to impact | 12691/B | mm | | ≥1200 | | | | | | | |
| Hail resistance | 13583 | m/s | | ≥30(*) | | | | | | | |
| Water tightness (60kPa) | 1928 | | | Absolute | | | | | | | |
| Joint strength | | | | | | | | | | | |
| • Tensile strength | 12317-2 | N/cm | | Compliant (specimen fails outside bond area) | | | | | | | |
| • Peeling | 12316-2 | N/cm | | ≥58 | | | | | | | |
| Durability | | | | | | | | | | | |
| Resistance to artificial UV light | 1297-5000 h | | | No surface damage or significant changes in cold flexibility as per EN 495/5 | | | | | | | |
| Heat aging in area | | | | | | | | | | | |
| Change in tensile strength | 12311-2 | $\Delta\%$ | | -5 | | | | | | | |
| Change in elongation at break | 12311-2 | $\Delta\%$ | | -5 | | | | | | | |
| Wind load resistance (wind suction test) (UEAtc) | | | | | | | | | | | |
| Mechanically retained system | Pa | | | | ≥6000 | | | | | | |
| Reaction to fire | 13501-1 | | | Class F | | | | | | | |
| Resistance to algae and microorganisms | ISO 846 Level 2 | | | | Compliant | | | | | | |
| Root resistance | 13948 | | | Passes the test | | | | | | | |
| Contact with drinking water (DW) | Italian Ministerial Decree 26-04-93 n. 220 - 0.J. no. 162 / 13-07-1993 and subsequent amendments | | | Suitable | | | | | | | |

Notes: (1) Tolerances as per EN 13956 and/or UEAtc Directives.

- (2) Not tested at lower temperatures.
- (*) Not tested at higher speeds.

| PRODUCTION STANDARDS | | | | | | | | | | |
|-----------------------|----|--------------|------|------|------|--|--|--|--|--|
| Thickness(*) | mm | 1,2 | 1,5 | 1,8 | 2,0 | | | | | |
| Width | m | 2,10 | 2,10 | 2,10 | 2,10 | | | | | |
| Length ^(*) | m | 25 | 25 | 20 | 20 | | | | | |
| Colour | | Grey / Black | | | | | | | | |

 $^{(\}star)$ Different thicknesses and lengths are available on demand and for minimum quantities.

Rev. 00 (11-15)

As IMPER ITALIA srl has no control over how or where its products are supplied (e.g., over substrates, service conditions, or compliance with instructions), the company cannot accept any liability arising from the use of its product or the results obtained. IMPER ITALIA srl pursues a policy of continuous product improvement. As a result, the company reserves the right to make any necessary changes to the information contained in this publication at any time and without notice.











Imper Italia srl Via Volta, 8 · 10071
Frazione Mappano · Borgaro (TO) Italy
Tel (+39) 011 222.54.99 · Fax (+39) 011 222.54.80
export@imper.it · www.imper.it