

## EDILGRID W 80/30



Woven geogrid made of high tenacity polyester yarn coated with PVC.

Physical properties	Standard		Value	Units	Tolerance %	Tolerance (units)
Mass per unit area	[EN ISO 9864]		367	g/m <sup>2</sup>	+/- 10	+/- 37
Mesh size		MD	20	mm	+/- 12	+/- 2
		CMD	24	mm	+/- 12	+/- 3
Yarn type		PES				
Type of coating		PVC				

Mechanical properties	Standard		Value	Units	Tolerance %	Tolerance (units)
Tensile strength	[EN ISO 10319]	MD	85	kN/m	- 6	- 5
	[EN ISO 10319]	CMD	33	kN/m	- 9	- 3
Elongation at maximum load	[EN ISO 10319]	MD	11	%	+/- 18	+/- 2
	[EN ISO 10319]	CMD	10	%	+/- 20	+/- 2
Strength at 2% of elongation	[EN ISO 10319]	MD	27,0	kN/m	- 11	- 3,0
	[EN ISO 10319]	CMD	9,0	kN/m	- 22	- 2,0
Strength at 3% of elongation	[EN ISO 10319]	MD	35,0	kN/m	- 9	- 3,2
	[EN ISO 10319]	CMD	12,0	kN/m	- 17	- 2,0
Strength at 5% of elongation	[EN ISO 10319]	MD	53,0	kN/m	- 6	- 3,2
	[EN ISO 10319]	CMD	18,0	kN/m	- 11	- 2,0

### Durability properties

Weathering resistance	[EN 12224]	To be covered within 15 days from the day of installation.
Resistance to hydrolysis	[EN 12447]	Forecast minimum durability of 100 years in natural ground with 4<pH<9 and soil temperature < 25°C.

The values given are an average obtained in our laboratories and in official testing institutes.  
The confidence level is 95%  
The right is reserved to make changes any time without notice.

MD = Machine Direction/Longitudinale; CMD = Cross Machine Direction/Trasversale; NA = Not Applicable/Non Applicabile

Ref.

Cod. 001283  
Rev.3  
Data Rev.: 07-04-2018

Approved by CQ



Approved by UT

