

GEODREN PEIT 150



1213-CPD-3275

Nonwoven geotextile made by polyester, needlepunched and calandered, produced without using of any glues or chemical binders and post-consumer raw material.

Physical properties	Standard	Value	Units	Tolerance %	Tolerance (units)
Mass per unit area	[EN ISO 9864]	150	g/m ²	+/- 10	+/- 15
Thickness	[EN ISO 9863-1] 2 kPa	0,90	mm	+/- 20	+/- 0,18
	[EN ISO 9863-1] 20 kPa	0,70	mm	+/- 20	+/- 0,14
	[EN ISO 9863-1] 200 kPa	0,40	mm	+/- 20	+/- 0,08

Mechanical properties	Standard	Value	Units	Tolerance %	Tolerance (units)
Tensile strength	[EN ISO 10319] MD	1,2	kN/m	- 15	- 0,2
	[EN ISO 10319] CMD	1,2	kN/m	- 15	- 0,2
Elongation at maximum load	[EN ISO 10319] MD	50	%	+/- 30	+/- 15
	[EN ISO 10319] CMD	60	%	+/- 30	+/- 18
Static puncture resistance (CBR)	[EN ISO 12236]	0,20	kN	- 30	- 0,06
Dynamic puncture resistance	[EN ISO 13433]	> 50	mm		

Hydraulic properties	Standard	Value	Units	Tolerance %	Tolerance (units)
Velocity index	[EN ISO 11058]	110	mm/s	- 30	- 33
Characteristic opening size	[EN ISO 12956]	65	µm	+/- 30	+/- 20

Durability properties	Standard	Value	Units	Tolerance %	Tolerance (units)
Weathering resistance	[EN 12224]	To be covered within 1 day from the day of installation.			
Service life		Forecast minimum durability of 5 years in natural ground with 4<pH<9 and soil temperature < 25°C.			

The values given are an average obtained in our laboratories and in official testing institutes.
 The confidence level is 95%
 The right is reserved to make changes any time without notice.

MD = Machine Direction/Longitudinale; CMD = Cross Machine Direction/Trasversale; NA = Not Applicable/Non Applicabile

Ref.
 Cod. 000003
 Rev.2
 Data Rev.: 26-01-2011

Prepared by CQ

Approved by UT