

# GEODREN PEIT 200



1213-CPD-3275

Nonwoven geotextile made by polyester, needlepunched and calandered, produced without using of any glues or chemical binders and post-consumer raw material.

Physical properties	Standard	Value	Units	Tolerance %	Tolerance (units)
Mass per unit area	[EN ISO 9864]	200	g/m <sup>2</sup>	+/- 10	+/- 20
Thickness	[EN ISO 9863-1] 2 kPa	1,10	mm	+/- 20	+/- 0,22
	[EN ISO 9863-1] 20 kPa	0,80	mm	+/- 20	+/- 0,16
	[EN ISO 9863-1] 200 kPa	0,50	mm	+/- 20	+/- 0,10

Mechanical properties	Standard	Value	Units	Tolerance %	Tolerance (units)
Tensile strength	[EN ISO 10319] MD	1,8	kN/m	- 15	- 0,3
	[EN ISO 10319] CMD	1,8	kN/m	- 15	- 0,3
Elongation at maximum load	[EN ISO 10319] MD	50	%	+/- 30	+/- 15
	[EN ISO 10319] CMD	60	%	+/- 30	+/- 18
Static puncture resistance (CBR)	[EN ISO 12236]	0,30	kN	- 30	- 0,09
Dynamic puncture resistance	[EN ISO 13433]	> 50	mm		

Hydraulic properties	Standard	Value	Units	Tolerance %	Tolerance (units)
Velocity index	[EN ISO 11058]	100	mm/s	- 30	- 30
Characteristic opening size	[EN ISO 12956]	60	µm	+/- 30	+/- 18

Durability properties	Standard	Value	Units	Tolerance %	Tolerance (units)
Weathering resistance	[EN 12224]	To be covered within 1 day from the day of installation.			
Service life		Forecast minimum durability of 5 years in natural ground with 4<pH<9 and soil temperature < 25°C.			

The values given are an average obtained in our laboratories and in official testing institutes.  
 The confidence level is 95%  
 The right is reserved to make changes any time without notice.

MD = Machine Direction/Longitudinale; CMD = Cross Machine Direction/Trasversale; NA = Not Applicable/Non Applicabile

**Ref.**  
 Cod. 000004  
 Rev.2  
 Data Rev.: 26-01-2011

**Prepared by CQ**

**Approved by UT**