

GEODREN PPST 150



1213-CPD-3269

Nonwoven geotextile made by high tenacity polypropylene staples, UV stabilized, needlepunched and calandered, produced without using of any glues or chemical binders and post-consumer raw material.

Physical properties	Standard		Value	Units	Tolerance %	Tolerance (units)
Mass per unit area	[EN ISO 9864]		150	g/m ²	+/- 10	+/- 15
Thickness	[EN ISO 9863-1] 2 kPa		1,00	mm	+/- 20	+/- 0,20
	[EN ISO 9863-1] 20 kPa		0,80	mm	+/- 20	+/- 0,16
	[EN ISO 9863-1] 200 kPa		0,60	mm	+/- 20	+/- 0,12
Mechanical properties	Standard		Value	Units	Tolerance %	Tolerance (units)
Tensile strength	[EN ISO 10319] MD		12,0	kN/m	- 10	- 1,2
	[EN ISO 10319] CMD		12,0	kN/m	- 10	- 1,2
Elongation at maximum load	[EN ISO 10319] MD		55	%	+/- 30	+/- 17
	[EN ISO 10319] CMD		60	%	+/- 30	+/- 18
Energy absorption index	[EN ISO 10318]		3,50	kJ/m ²	- 20	- 0,70
Static puncture resistance (CBR)	[EN ISO 12236]		1,90	kN	- 10	- 0,19
Dynamic puncture resistance	[EN ISO 13433]		26	mm	+ 20	+ 5
Hydraulic properties	Standard		Value	Units	Tolerance %	Tolerance (units)
Velocity index	[EN ISO 11058]		100	mm/s	- 30	- 30
In-plane flow capacity	[EN ISO 12958]		1,60	10-3 l/ms	- 30	- 0,48
Characteristic opening size	[EN ISO 12956]		90	µm	+/- 30	+/- 27
Durability properties						
Weathering resistance	[EN 12224]		To be covered within 30 days from the day of installation.			
Residual strength after weathering test	[EN 12226]		Residual strength higher than 60% of initial resistance.			
Resistance to oxidation	[EN ISO 13438]		Forecast minimum durability of 25 years in natural ground with 4<pH<9 and soil temperature < 25°C.			
Residual strength after oxidation test	[EN 12226]		Residual strength greater than or equal to 50% of initial resistance.			

The values given are an average obtained in our laboratories and in official testing institutes.
 The confidence level is 95%
 The right is reserved to make changes any time without notice.

MD = Machine Direction/Longitudinale; CMD = Cross Machine Direction/Trasversale; NA = Not Applicable/Non Applicabile

Ref.
 Cod. 000058
 Rev.2
 Data Rev.: 24-08-2011

Prepared by CQ

Approved by UT