

# MasterSeal 912

Hydro-expansive, polyurethane mastic for the sealing of joints against seeping water.

## MATERIAL DESCRIPTION

MasterSeal 912 is a hydro-expansive, single-component polyurethane mastic for sealing joints against water seepage.



## FIELDS OF APPLICATION

Sealing against water seepage in:

- construction joints;
- joints between prefabricated elements;
- holes for pipes;
- H-section steel pillars;
- underground structures.

It can also be used as an adhesive for joints made with hydro-expansive rubber MasterSeal 910, especially on rough or wet surfaces.



## FEATURES AND BENEFITS

- single-component, easy to apply: it can be applied with a common sealant gun;
- it does not require primers on substrates made of concrete, PVC, HDPE, steel, etc.;
- not solvent-based;
- it can be applied to both dry and damp surfaces;

- it is also suitable for underwater applications;
- permanent hydro-expansive and flexible properties;
- it follows the movements of joints and structures;
- chemical-resistant, especially in the presence of oil, grease and petroleum by-products.

## TYPICAL PERFORMANCE

| Requirements and test methods  | Performance                           |
|--|---------------------------------------|
| Expansion in distilled water after 15 days at 20°C                       | approx. 320 % of the initial volume   |
| Expansion in salt water (14% salt solution) after approximately 28 days) | approx. 80-90 % of the initial volume |
| Resistance to positive hydraulic pressure                                | > 10 bar                              |
| Elongation at break, ISO 527-2   | approx. 800%                          |
| Tensile strength, ISO 527-2  | 2.45 MPa                              |

## CHEMICAL RESISTANCES

| Aggressive             | Stability             | Expansion    |
|------------------------|-----------------------|--------------|
| Lead-free fuel         | Resistant with fading | approx. 45%  |
| Diesel oil             | Resistant with fading | approx. 2%   |
| Toluene                | Resistant             | approx. 140% |
| Xylene                 | Resistant             | approx. 85%  |
| Methanol 50%           | Resistant             | approx. 400% |
| Isopropanol 50%        | Resistant             | approx. 500% |
| Ethylene acetate       | Resistant             | approx. 195% |
| Methyl isobutyl ketone | Resistant             | approx. 85%  |
| Acetic acid 10%        | Limited resistance    | approx. 150% |
| Sulphuric acid 10%     | Resistant             | approx. 190% |
| Sulphuric acid 20%     | Resistant             | approx. 210% |
| Sulphuric acid 26%     | Resistant             | approx. 25%  |

## PACKAGING

310-ml cartridges and 600-ml rolls.

## STORAGE

Store the material in the original containers, in a dry and covered place at a temperature between 15 and 25°C. Do not expose to direct sunlight.

# MasterSeal 912

Hydro-expansive, polyurethane mastic for the sealing of joints against seeping water.

## APPLICATION SHEET

### TEMPERATURE

It can be applied when the ambient temperature is between +5°C and +40°C.

### PREPARING THE SUBSTRATE

Correct preparation of the substrate is essential to successful application.

The application surface must be structurally sound, without any prominent irregularities, clean and clear of any dust, oils, grease, other contaminating substances. Repair any imperfections with a suitable product from the MasterEmaco line, and eliminate any trace of liquid water from the surface.

### APPLICATION

Break the seal on the cartridge, attach the nozzle and cut it to the required diameter. MasterSeal 912 can be applied with a normal sealant gun and must be pressed into the substrate.

Apply a consistent and continuous amount of product onto the substrate inside the element being sealed.



### CLEANING

Non-hardened product can be easily removed with solvent. Hardened product can only be removed mechanically.

### WARNING

With underwater use or on very wet substrates, cast the concrete within a maximum of 6 hours to prevent premature expansion. Make sure the product is completely incorporated into the concrete casting. Ensure concrete coverage of at least 8 cm.

### SAFETY INSTRUCTION

For information on the correct and safe use, transport, storage and disposal of the product, consult the most recent Safety Data Sheet.

### OTHER SERVICES

For price analysis, specifications, supplementary brochures, references, reports and technical assistance, visit the website [www.master-builders-solutions.com/it-it](http://www.master-builders-solutions.com/it-it) or contact [infomac@mbcc-group.com](mailto:infomac@mbcc-group.com).

Scan the QR code to visit the product page and download the latest version of this datasheet.

| Technical data                          |                       |
|---|-----------------------|
| Density, DIN 53504                      | approx. 1.45 kg/litre |
| Resistance to vertical sag, Boeing test | < 5 mm                |
| To the touch                            | approx. 10 hours      |
| Hardening                               | approx. 16 hours      |
| Flash point, Pensky-Martens Method      | > 130 °C              |
| Resistance to temperature               | -30°C – 80°C          |

### HOLES FOR PIPES

Remove the concrete from around the pipe by a depth of at least 3 cm. Apply the product around the hole with a minimum thickness of 10 mm.

Fill the remainder with MasterSeal 590.

# MasterSeal 912

---

Hydro-expansive, polyurethane mastic for the sealing of joints against seeping water.

---

Since 16/12/1992, Master Builders Solutions Italia Spa has been operating under a Certified Quality System compliant with the UNI EN ISO 9001 Standard. Furthermore, the Environmental Management System is certified according to the UNI EN ISO 14001 Standard and the Safety Management System is certified according to the UNI ISO 45001 Standard.

**Master Builders Solutions Italia Spa**

Via Vicinale delle Corti, 21 – 31100 Treviso – Italia

T +39 0422 429200 F +39 0422 421802

[www.master-builders-solutions.com/it-it](http://www.master-builders-solutions.com/it-it)

e-mail: [infomac@mbcc-group.com](mailto:infomac@mbcc-group.com)

For further information, please consult the local Technician of Master Builders Solutions. The technical advice on how to use our products, either written or verbally given, are based on the current state of our scientific and practical expertise, and does not imply the assumption of any guarantee and/or responsibility for the final results of works executed using our products.

Therefore, the customer is not exempted from the exclusive task and responsibility of verifying the suitability of our products for the intended use and purposes.

This version supersedes all the previous ones.